

Abstract No:**Physical Sciences****HYDROTHERMAL SYNTHESIS AND CHARACTERIZATION OF MORDENITE****M.K.N. Ranasinghe^{1,*}, I.P.L. Jayarathne² and W.M.A.T. Bandara¹**¹*Department of Chemistry, Faculty of Science, University of Peradeniya, Peradeniya, Sri Lanka*²*National Institute of Fundamental Studies, Kandy, Sri Lanka
rkumu8@gmail.com*

Mordenite is one of the most highly siliceous zeolites which has an ideal composition of $\text{Na}_8\text{Al}_8\text{Si}_{40}\text{O}_{96}\cdot 24\text{H}_2\text{O}$. Mordenite has been used mainly as a catalyst for many industrially important reactions such as alkylation, hydrocracking, hydroisomerization, dewaxing, reforming, and cracking. Mordenite has also been used in the absorptive separation of gas or liquid mixtures, where it is used as a molecular sieve. Even though mordenite occurs as a natural mineral, synthetic mordenite are better suited to meet many of the industrial requirements. Main reasons behind this are its purity and controlled pore structure. In this work, mordenite was synthesized by a hydrothermal synthesis method. Hydrothermal synthesis is commonly used in the synthesis of aluminosilicate zeolites due to its advantages over other methods such as effective solvation ability of water, increased solubility of reactants and increased nucleation. Effect of different parameters in the synthesis of mordenite was investigated by adjusting the gel composition and optimizing parameters such as crystallization temperature (170 °C, 180 °C, 190 °C and 200 °C), crystallization time (24 h, 36 h, 48 h and 72 h) and aging time (2 h, 4 h and 8 h). Mordenite was successfully synthesized in the absence of seeds and in the absence of organic templates at 170 °C, 48 h of crystallization time and 4 h of aging of the synthesis mixture. Gel composition of the mixture was $6\text{Na}_2\text{O}:\text{Al}_2\text{O}_3:30\text{SiO}_2:780\text{H}_2\text{O}$. Mordenite was also successfully modified with Fe and Zn to get Fe-MOR and Zn-MOR respectively. Modification with iron was done by a solid ion exchange method using FeSO_4 and zinc modification was done by a wet ion exchange method using a $\text{Zn}(\text{NO}_3)_2$ solution. The products were characterized using PXRD, FTIR, XRF and particle size analyzing techniques. Hence this work is a study of an eco-friendly method for the synthesis of mordenite under laboratory conditions.

Financial assistance from National Institute of Fundamental Studies, Sri Lanka (Grant No NRC 10 090) is acknowledged.

Keywords: Hydrothermal synthesis, Mordenite, Zeolite.