




UNIVERSITY OF
KELANIYA

Faculty of
Graduate Studies

22nd INTERNATIONAL POSTGRADUATE RESEARCH CONFERENCE (IPRC) 2022

**"RESEARCH AND INNOVATIONS IN CRISIS
SITUATIONS"**



ABSTRACTS

Organized by
THE FACULTY OF GRADUATE STUDIES
University of Kelaniya, Sri Lanka

Structural analysis of $\text{LiNi}_{1/3}\text{Mn}_{1/3}\text{Co}_{1/3}\text{O}_2$, $\text{Li}_{0.96}\text{Na}_{0.04}\text{Ni}_{1/3}\text{Mn}_{1/3}\text{Co}_{1/3}\text{O}_2$ and $\text{Li}_{0.96}\text{K}_{0.04}\text{Ni}_{1/3}\text{Mn}_{1/3}\text{Co}_{1/3}\text{O}_2$ materials synthesized by Pechini method

Fernando W. T. R. S.^{1*}, Amaraweera T. H. N. G.², Wijayasinghe A.¹

Layered tri-transition metal oxides, specially $\text{LiNi}_{1/3}\text{Mn}_{1/3}\text{Co}_{1/3}\text{O}_2$ (NMC 333), have become a promising alternative to LiCoO_2 electrode material in the rechargeable Lithium-Ion Battery (LIB). The electrochemical performances of NMC 333 mainly depend on its crystallographic structural properties including lattice parameters, the unit-cell, c/a ratio, volume, crystallite size (D), dislocation density (δ), and lattice strain. This study aims to synthesize $\text{LiNi}_{1/3}\text{Mn}_{1/3}\text{Co}_{1/3}\text{O}_2$, $\text{Li}_{0.96}\text{Na}_{0.04}\text{Ni}_{1/3}\text{Mn}_{1/3}\text{Co}_{1/3}\text{O}_2$ and $\text{Li}_{0.96}\text{K}_{0.04}\text{Ni}_{1/3}\text{Mn}_{1/3}\text{Co}_{1/3}\text{O}_2$ materials and study their structural properties. The Pechini method was used for powder synthesis in this study. The synthesized materials were characterized using X-ray diffraction (XRD). X-ray characterization confirmed the formation of only the single-phase layered hexagonal lattice ($\alpha\text{-NaFeO}_2$ -type) structure without any impurity phase for all these prepared materials. Interestingly, while confirming the formation of layered structures, a better splitting of the (006)/(102) and (108)/(110) peaks appeared for $\text{Li}_{0.96}\text{K}_{0.04}\text{Ni}_{1/3}\text{Mn}_{1/3}\text{Co}_{1/3}\text{O}_2$ than that of $\text{LiNi}_{1/3}\text{Mn}_{1/3}\text{Co}_{1/3}\text{O}_2$ and $\text{Li}_{0.96}\text{Na}_{0.04}\text{Ni}_{1/3}\text{Mn}_{1/3}\text{Co}_{1/3}\text{O}_2$ in the diffractograms. The lattice parameters, i.e. a, c, c/a, the unit-cell volume, the crystallite size (D), and dislocation density (δ) are $2.8641(\text{\AA})$, $14.2143(\text{\AA})$, 4.9629 , $100.979(\text{\AA}^3)$, 77.45 nm , $1.666 \times 10^{14} \text{ m}^{-2}$, for $\text{LiNi}_{1/3}\text{Mn}_{1/3}\text{Co}_{1/3}\text{O}_2$. While they are $2.8675(\text{\AA})$, $14.2317(\text{\AA})$, 4.9630 , $101.347(\text{\AA}^3)$, 85.06 nm , $1.382 \times 10^{14} \text{ m}^{-2}$ for $\text{Li}_{0.96}\text{Na}_{0.04}\text{Ni}_{1/3}\text{Mn}_{1/3}\text{Co}_{1/3}\text{O}_2$ and $2.869(\text{\AA})$, $14.2421(\text{\AA})$, 4.9641 , $101.528(\text{\AA}^3)$, 128.38 nm , $0.606 \times 10^{14} \text{ m}^{-2}$ for $\text{Li}_{0.96}\text{K}_{0.04}\text{Ni}_{1/3}\text{Mn}_{1/3}\text{Co}_{1/3}\text{O}_2$ respectively. It is also observed that the lattice parameters, the unit-cell volume, c/a, and the crystallite size are increased with the substitution of Li^+ by Na^+ and K^+ . It may be due to the radii of Na^+ and K^+ are bigger than that of Li^+ and that will pave the way for increasing the interlayer space of the substituted materials with the substitution of bigger ions. The c/a ratio constitutes a direct indication of the cation mixing. $\text{Li}_{0.96}\text{Na}_{0.04}\text{Ni}_{1/3}\text{Mn}_{1/3}\text{Co}_{1/3}\text{O}_2$ and $\text{Li}_{0.96}\text{K}_{0.04}\text{Ni}_{1/3}\text{Mn}_{1/3}\text{Co}_{1/3}\text{O}_2$ exhibit higher c/a values than $\text{LiNi}_{1/3}\text{Mn}_{1/3}\text{Co}_{1/3}\text{O}_2$, supporting the observation that the substituting bigger ions such as Na^+ and K^+ into $\text{LiNi}_{1/3}\text{Mn}_{1/3}\text{Co}_{1/3}\text{O}_2$ suppresses the cation mixing and forms a well-defined layered structure. The micro-strain calculated for the $\text{LiNi}_{1/3}\text{Mn}_{1/3}\text{Co}_{1/3}\text{O}_2$, $\text{Li}_{0.96}\text{Na}_{0.04}\text{Ni}_{1/3}\text{Mn}_{1/3}\text{Co}_{1/3}\text{O}_2$ and $\text{Li}_{0.96}\text{K}_{0.04}\text{Ni}_{1/3}\text{Mn}_{1/3}\text{Co}_{1/3}\text{O}_2$ are 1.38×10^{-2} , 2.17×10^{-2} and 1.46×10^{-2} , respectively. This implies a slight difference in the crystallinity of the materials, as the micro-strain was slightly affected by substituting Na^+ and K^+ . Crystallite size (D) was 77.45 nm , 85.06 nm and 128.38 nm for $\text{LiNi}_{1/3}\text{Mn}_{1/3}\text{Co}_{1/3}\text{O}_2$, $\text{Li}_{0.96}\text{Na}_{0.04}\text{Ni}_{1/3}\text{Mn}_{1/3}\text{Co}_{1/3}\text{O}_2$ and $\text{Li}_{0.96}\text{K}_{0.04}\text{Ni}_{1/3}\text{Mn}_{1/3}\text{Co}_{1/3}\text{O}_2$, respectively. It exhibits an increment of crystallite size, indicating a lowering of the dislocation density with the substitution of bigger ions. Altogether, this study reveals that substituting Li^+ with bigger ions of Na^+ and K^+ is improving the structural stability of NMC 333.

Keywords: NMC materials, Na doping, K doping, Li-ion battery, Pechini method

*This version cannot be considered as evidence of this publication - final version is available at <https://conf.kln.ac.lk/iprc/>

¹ National Centre for Advanced Battery Research, National Institute of Fundamental Studies, Kandy, Sri Lanka

² Department of Applied Earth Sciences, Uva Wellassa University

* roshanrsff@gmail.com