



The 14<sup>th</sup> International Conference on

# Sustainable Built Environment -2023



*The Kandy Conference*



## BOOK OF ABSTRACTS

Editors

Prof. Ranjith Dissanayake | Dr. Pradeep Gajanayake



**Abstract Book of the 14<sup>th</sup> International Conference on Sustainable Built Environment – (ICSBE) 2023**

**Vision**

To drive innovative research for tomorrow's development

**Mission**

To meet colleagues, experts, and friends in the field and to exchange ideas and those about research development work, concepts and practical ideas in structural, Construction and management

All right reserved

No part of this publication may be reproduced, stored in a retrieval system, transmitted in any form or by any means, electronic, mechanical, photocopy, and recording or otherwise, without prior permission of all the editors and conference chair

ISSN 3021-6966

Published by:

Graduate Associate Professionals (Pvt) Ltd  
Science Tower 120/10A, Vidya Mawatha, Colombo 07

ICSBE 2023-89

**ELECTROCHEMICAL PERFORMANCE OF CuO ANODE MATERIAL SYNTHESIZED BY CHEMICAL PRECIPITATION METHOD FOR RECHARGABLE LITHIUM-ION BATTERIES****W. T. R. S. Fernando<sup>1\*</sup>, T. H. N. G. Amaraweera<sup>2</sup>, H. W. M. A. C. Wijayasinghe<sup>1</sup>**<sup>1</sup> National Center for Advanced Battery Research, National Institute of Fundamental Studies, Sri Lanka.<sup>2</sup> Department of Applied Earth Sciences, Uva Wellassa University, Sri Lanka.

\*Correspondence E-mail: roshanrsff@gmail.com, TP: +94713638603

**Abstract:** CuO has received more attention for the anode application of the rechargeable Lithium-Ion Battery (LIB) than the other competing materials because of its high theoretical capacity ( $674 \text{ mAhg}^{-1}$ ), good capacity retention, affordability, non-toxicity and ease of storage. The electrochemical performance of CuO mainly depends on crystallinity and morphology, which significantly depend on the synthesizing technique. Simple and convenient chemical precipitation technique, which is a promising technique that enhances the crystallinity with favorable morphology for electrode materials, has not been studied. Therefore, this study aims for synthesizing CuO anode materials by the chemical precipitation technique, with improved crystallinity and morphology. The coin cells were assembled in an argon-filled glove box with anode electrodes fabricated with synthesized CuO, lithium as the reference electrode and counter electrodes together with the non-aqueous electrolyte of 1M LiPF<sub>6</sub> in ethylene carbonate and dimethyl carbonate (1:1 wt%). The electrochemical performances have been analyzed by galvanostatic charge- discharge measurements. It was found that CuO electrode exhibited a high initial discharge capacity of  $3371.9 \text{ mAhg}^{-1}$  at a rate of C/5. The electrode showed a discharge capacity of  $442.9 \text{ mAhg}^{-1}$  with Columbic efficiency of 97.4%, after 50 cycles. Even though it reported a higher irreversible capacity of  $2002.2 \text{ mAhg}^{-1}$  at the 1<sup>st</sup> cycle, it lowered down to  $11.4 \text{ mAhg}^{-1}$  at the 50<sup>th</sup> cycle. The enhanced electrochemical performance can mainly be attributed for the enhanced contact surface area for CuO and electrolyte. It could have led to the enhanced contact between CuO and electrolyte and by decreasing diffusion lengths for lithium ions. Electrochemical impedance spectroscopy and cyclic voltammetry analyses also showed improved electrochemical performance. Altogether, this study reveals that CuO synthesized by simple, cost - effective, non - toxic and environmentally friendly chemical precipitation method has very promising electrochemical performance for the anode application of next-generation high - performance LIBs.

**Keywords:** Anode materials; CuO; Chemical precipitation; Li-ion battery