

See discussions, stats, and author profiles for this publication at: <https://www.researchgate.net/publication/381652425>

ELECTROCHEMICAL PERFORMANCE OF CuO ANODE MATERIAL SYNTHESIZED BY CHEMICAL PRECIPITATION TECHNIQUE AT DIFFERENT TEMPERATURES, FOR RECHARGEABLE LITHIUM-ION BATTERIES

Conference Paper · June 2024

CITATIONS

0

READS

10

4 authors:



Roshan Fernando

University of Kelaniya

24 PUBLICATIONS 1 CITATION

SEE PROFILE



Niranjala Gayani Amaraweera

Uva Wellassa University

55 PUBLICATIONS 78 CITATIONS

SEE PROFILE



R. P. Wijesundera

University of Kelaniya

99 PUBLICATIONS 747 CITATIONS

SEE PROFILE




Athula Chandana Wijayasinghe

National Institute of Fundamental Studies

86 PUBLICATIONS 447 CITATIONS

SEE PROFILE



Second International Conference on

Frontiers in Chemical Technology

20 - 22 June, 2024

**Hotel Marino Beach
590, Marine Drive, Colombo 03**

FCT2 - 2024

Conference Proceedings

ELECTROCHEMICAL PERFORMANCE OF CuO ANODE MATERIAL SYNTHESIZED BY CHEMICAL PRECIPITATION TECHNIQUE AT DIFFERENT TEMPERATURES, FOR RECHARGEABLE LITHIUM-ION BATTERIES

W.T.R.S. Fernando^{1*}, T.H.N.G. Amaraweera^{1,2}, R.P. Wijesundera³ and H.W.M.A.C. Wijayasinghe¹

¹National Center for Advanced Battery Research, National Institute of Fundamental Studies, Kandy, Sri Lanka

²Department of Applied Earth Sciences, Uva Wellassa University, Sri Lanka

³Department of Physics and Electronics, University of Kelaniya, Sri Lanka

*roshanrff@gmail.com

Copper oxide (CuO) is a desirable anode material for the rechargeable lithium ion battery (LIB) due to its high theoretical capacity (675 mA h g^{-1}), good capacity retention, affordability, non-toxicity, and ease of storage. The electrochemical performance of CuO mainly depends on morphology and anode/current collector interfacial properties, which can significantly be manipulated by the synthesizing technique. Therefore, this study aims for preparing CuO anode materials by a chemical precipitation technique with enhanced crystallinity, morphology, and anode/current collector interfacial properties. The lithium ion rechargeable coin cells were assembled in an argon-filled glove box with anodes fabricated with synthesized CuO at different bath temperatures (25°C , 50°C and 75°C). The galvanostatic charge-discharge characterization study of the CuO electrodes reported high initial discharge capacities of 2827.1, 3371.9 and 2009.9 mA h g^{-1} with a Coulombic efficiency (CE) of 58%, 40.6% and 33.1% at a rate of C/5 for those synthesized at 25°C , 50°C and 75°C bath temperatures, respectively. Further it showed discharge capacities of 466.2, 442.9 and 232.3 mA h g^{-1} with Coulombic efficiencies of 88.7, 97.4 and 95.9% after 50 cycles for those synthesized at 25°C , 50°C and 75°C bath temperatures, respectively. The results revealed that CuO anodes prepared in this study show considerably better electrochemical performance compared to that of the previously reported. However, the best performance was reported by CuO synthesized at 25°C compared to that synthesized at 50°C and 75°C . The enhanced electrochemical performance could be related to the enhanced contact surface area between CuO and electrolyte and anode/current collector interfacial properties. It could have led to the enhanced contact between CuO and electrolyte, hence reducing diffusion length for lithium ions. The enhanced anode/current collector interfacial properties may facilitate for electrons to transfer between current collector and active material. Accordingly, the present study reveals that the chemical precipitation method is a promising technique, which improves the crystallinity with favorable morphology and anode/current collector interfacial properties of electrode materials indicating a high potential for the anode application in next-generation high-performance LIBs.

Keywords: Anode materials, chemical precipitation, CuO, Li-ion battery